



Chen, C., Ding, P., mura, M., Chen, Y., Sun, Y., Kantorovich, L. N., Gersen, H., Besenbacher, F., & Yu, M. (2018). Formation of Hypoxanthine Tetrad by Reaction with Sodium Chloride: From Planar to Stereo. *Angewandte Chemie - International Edition*, 57(49), 16015-16019. <https://doi.org/10.1002/anie.201808613>

Peer reviewed version

License (if available):  
Unspecified

Link to published version (if available):  
[10.1002/anie.201808613](https://doi.org/10.1002/anie.201808613)

[Link to publication record in Explore Bristol Research](#)  
PDF-document

This is the author accepted manuscript (AAM). The final published version (version of record) is available online via Wiley at <https://onlinelibrary.wiley.com/doi/abs/10.1002/anie.201808613> . Please refer to any applicable terms of use of the publisher.

## University of Bristol - Explore Bristol Research

### General rights

This document is made available in accordance with publisher policies. Please cite only the published version using the reference above. Full terms of use are available:  
<http://www.bristol.ac.uk/red/research-policy/pure/user-guides/ebr-terms/>

# Formation of Hypoxanthine Tetrad by Reaction with Sodium Chloride: From Planar to Stereo

*Chong Chen<sup>1,#</sup>, Pengcheng Ding<sup>1,2,#</sup>, Manuela Mura<sup>3</sup>, Yanghan Chen<sup>1,2</sup>, Ye Sun<sup>2</sup>, Lev N.*

*Kantorovich<sup>4</sup>, Henkjan Gersen<sup>5</sup>, Flemming Besenbacher<sup>6</sup>, and Miao Yu<sup>1,\*</sup>*

<sup>1</sup>State Key Laboratory of Urban Water Resource and Environment, School of Chemistry and Chemical Engineering, Harbin Institute of Technology, Harbin 150001, China

<sup>2</sup>Condensed Matter Science and Technology Institute, Harbin Institute of Technology, Harbin 150001, China

<sup>3</sup> School of Mathematics and Physics, University of Lincoln, Brayford Pool LN6 7TS, United Kingdom

<sup>4</sup> Department of Physics, King's College London, The Strand, London WC2R 2LS, United Kingdom

<sup>5</sup> H. H. Wills Physics Laboratory, University of Bristol, Bristol BS8 1TL, United Kingdom

<sup>6</sup> iNANO and Department of Physics and Astronomy, Aarhus University, Aarhus 8000, Denmark

Correspondence to: miaoyu\_che@hit.edu.cn


<sup>#</sup> These authors contributed equally to this work.

## 1. Experimental details


All experiments were conducted in a ultrahigh vacuum chamber equipped with a variable-temperature Aarhus scanning tunneling microscopy (STM).<sup>[1]</sup> The typical base pressure was  $1 \times 10^{-10}$  Torr. The Au(111) single-crystal sample was cleaned by repeated cycles of 0.8 KeV Argon ion bombardment and annealed at 800 K for 15 min. Hypoxanthine (HX, Shanghai Aladdin Biochemical Technology Co., Ltd, 99%) was sublimated from a thermal evaporator heated to  $\sim 410$  K and deposited onto clean Au(111) surface kept at room temperature (RT). All STM results were collected in the constant current mode at RT, with a bias voltage of 1.0-1.3 V and a tunneling current of 0.2-0.5 nA.

## 2. Calculation methods


Density functional theory (DFT) calculations were carried out using the Vienna *ab initio* simulation package (VASP).<sup>[2,3]</sup> The projector augmented wave (PAW) potentials were used to describe the interaction ionic cores and electrons and the Perdew-Burke-Ernzerhof (PBE) exchange-correlation density functional was used.<sup>[4]</sup> The dispersion interactions were considered within the dispersion-corrected DFT-D3 method of Grimme for the calculations when including the gold surface.<sup>[5]</sup> The force convergence criterion used for geometry relaxations was 0.02 eV/Å. The simulated STM images were based on the Tersoff-Hamann method.<sup>[6,7]</sup> The molecular clusters were optimized with the Au (111) substrate included. Partial charges were evaluated using Bader charge analysis based on DFT calculated electronic density.




**Figure S1.** Disordered structure of HX molecules when depositing alone on Au(111) without post-annealing.




**Figure S2.** Top and side views of the electronic density of the close-packed structure of HX on Au(111) at the isosurface value of  $0.006 \text{ e}\text{\AA}^{-3}$ , showing no charge transfer with the substrate.




**Figure S3.** The close-packed structure of HX on Au(111), obtained after annealing, clearly showing a corrugation corresponding to the herringbone reconstruction of pristine clean Au(111) and hence indicating a weak HX-Au interaction in this case.



**Figure S4.** A 2-D domain of the planar HX-tetrads, where the edges of the networks are terminated by the tetrads (highlighted by dotted boxes).



**Figure S5.** (a-b) Large-scale and zoom-in images of an anticlockwise arranged windmill-like tetramer network, with each tetramer comprised of four L-chiral HX. (c-d) Model of the two homochiral tetrads composed by L- and D-chiral HXs and one Na in the tetrad center. (e-f) Close view of the networks of L- and D-tetrads superimposed with the calculated model.



**Figure S6.** (a) Starting planar configuration and (b) relaxed structure of the calculated non-planar HX-tetrads with Na on the Au(111) surface.

## References

- [1] E. Laegsgaard, L. Österlund, P. Thostrup, P. B. Rasmussen, I. Stensgaard, F. Besenbacher, *Rev. Sci. Instrum.* **2001**, 72, 3537–3542.
- [2] G. Kresse, J. Hafner, *Phys. Rev. B* **1993**, 48, 13115–13118.
- [3] G. Kresse, J. Furthmüller, *Phys. Rev. B* **1996**, 54, 11169–11186.
- [4] J. P. Perdew, K. Burke, M. Ernzerhof, *Phys. Rev. Lett.* **1996**, 77, 3865–3868.
- [5] S. Grimme, *J. Comput. Chem.* **2006**, 27, 1787–1799.
- [6] J. Tersoff, D. Hamann, *Phys. Rev. B* **1985**, 31, 805–813.
- [7] D. E. Vanpoucke, G. Brocks, *Phys. Rev. B* **2008**, 77, 241308–241311.